

# DuPont™ Tyvek® HomeWrap® for Canada

## PHYSICAL PROPERTIES DATA SHEET

PROPERTIES	METHOD	DUPONT™ TYVEK® HOMEWRAP®
Air Penetration Resistance	ASTM E2178 (L/S/m <sup>2</sup> @75 Pa)	.01
	Gurley Hill (TAPPI T-460) (sec/100cc)	1080
	ASTM E1677	Type 1
Water Vapor Transmission	ASTM E96-05 Method B ng/Pa•S•m <sup>2</sup> (perms)	1720 30
Water Penetration Resistance	ATTCC 127 (cm)	210
Basis Weight	TAPPI T-410 (oz/yd <sup>2</sup> )	1.8
	(g/m <sup>2</sup> )	60
Breaking Strength	ASTM D882 (lbs/in)	30
	(N/mm)	5.4
Surface Burning Characteristics	ASTM E84 Flame Spread Index	5 Class A
	Smoke Developed Index	20 Class A
Ultra Violet Light Exposure (UV)		120 days (4 months)

Test results shown represent roll averages. Individual results may vary either above or below averages due to normal manufacturing variations, while continuing to meet product specifications.



For more information about DuPont™ Tyvek® Weatherization System products, please call 1-800-44-Tyvek or visit us at [www.Construction.Tyvek.com](http://www.Construction.Tyvek.com)

**WARNING:** DuPont™ Tyvek® is combustible and should be protected from an open flame and other high heat sources. If the temperature of DuPont™ Tyvek® reaches 750°F (400°C), it will burn and the fire may spread and fall away from the point of ignition.



*The miracles of science™*

DuPont™  
**Tyvek®**  
**HomeWrap®**