

DuPont™ Conpol™ 20B

Conpol™ resins Product Data Sheet

Description

Product Description	DuPont™ Conpol® 20B is a concentrated masterbatch made from an ethylene-methacrylic acid carrier resin. It is supplied in pellet form and is intended for blending with DuPont Surlyn® and Nucrel® resins to modify the surface properties of resulting films or coatings.
---------------------	--

Restrictions

Material Status	<ul style="list-style-type: none"> Commercial: Active
-----------------	--

Typical Characteristics

Uses	<ul style="list-style-type: none"> Packaging
Composition	20 % By Weight Anti-blocking agent
Applications	Coefficient of Friction modifier for the surface of films or coatings made from DuPont Surlyn® and Nucrel® resins.

Typical Properties

Physical	Nominal Values	Test Method(s)	
* Density ()	1.04 g/cm ³	ASTM D792	ISO 1183
* Melt Flow Rate (190°C/2.16kg)	6.5 g/10 min	ASTM D1238	ISO 1133
Thermal	Nominal Values	Test Method(s)	
* Melting Point (DSC)	99°C (210°F)	ASTM D3418	ISO 3146
Freezing Point (DSC)	84°C (183°F)	ASTM D3418	ISO 3146

Processing Information

General	
* Maximum Processing Temperature	310°C (590°F)
General Processing Information	Intended for use by blending into Surlyn® or Nucrel® resins utilized in the process of extrusion to produce blown / cast films, or extrusion coatings, either in monolayer or coextrusion. Concentrations will vary depending upon application, but normally range from the addition of 1 to 5% Conpol 20B into a given Surlyn® or Nucrel® resin.

FDA Status Information

CONPOL™ 20B Additive Resin is designed to modify the surface properties of films or coatings. This is a concentrated masterbatch product and is designed to be blended with the resin to be modified.

CONPOL™ 20B Additive Resin complies with U.S. Food and Drug Administration Regulation 21 CFR 177.1330(a) - Ionomeric resins, subject to the limitations and requirements therein. This Regulation describes polymers that may be used in contact with food, subject to the finished food-contact article meeting the extractive limitations under the intended conditions of use, as shown in paragraph (c) of the Regulation.

The information and certifications provided herein are based on data we believe to be reliable, to the best of our knowledge. The information and certifications apply only to the specific material designated herein as sold by DuPont and do not apply to use in any process or in combination with any other material. They are provided at the request of and without charge to our customers. Accordingly, DuPont cannot guarantee or warrant such certifications or information and assumes no liability for their use.

Regulatory Information

For Regulatory status outside the United States, please consult with your local DuPont representative.

Safety & Handling

For information on appropriate Handling & Storage of this polymeric resin, please refer to the Material Safety Data Sheet..

A Product Safety Bulletin, Material Safety Data Sheet, and/or more detailed information on extrusion processing and/or compounding of this polymeric resin for specific applications are available from your DuPont Packaging and Industrial Polymers representative.

Read and Understand the Material Safety Data Sheet (MSDS) before using this product

Regional Centres

DuPont operates in more than 70 countries. For help finding a local representative, please contact one of the following regional customer contact centers:

Americas

DuPont Company
Chestnut Run Plaza – Bldg. 730
974 Centre Road
Wilmington, Delaware
19805 U.S.A.
Toll-Free (USA): 1-800-628-6208
Telephone: 1-302-774-1000
Fax: 1-302-355-4013

Asia Pacific

DuPont China Holding Co., Ltd.
Shanghai Branch
399 Keyuan Road, Bldg. 11
Zhangjiang Hi-Tech Park
Pudong New District, Shanghai
P.R. China (Postcode: 201203)
Telephone +86 21 3862 2888
Fax +86-21-3862-2889

Europe / Middle East / Africa

DuPont de Nemours Int'l. S.A.
2, Chemin du Pavillon Box 50
CH-1218 Le Grand Saconnex
Geneva, Switzerland
Telephone +41 22 717 51 11
Fax +41 22 717 55 00

DuPont do Brasil, S.A.
Alameda Itapecuru, 506
06454-080 Barueri, SP Brasil
Telephone: +55 11 4166 8000
Fax: +55 11 4166 8736

<http://conpol.dupont.com>

The data listed here fall within the normal range of properties, but they should not be used to establish specification limits nor used alone as the basis of design. The DuPont Company assumes no obligations or liability for any advice furnished or for any results obtained with respect to this information. All such advice is given and accepted at the buyer's risk. The disclosure of information herein is not a licence to operate under, or a recommendation to infringe, any patent of DuPont or others. Since DuPont cannot

CAUTION: Do not use DuPont materials in medical applications involving implantations in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract that is consistent with DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative. You may also request a copy of DuPont POLICY Regarding Medical Applications H-50103-3 and DuPont CAUTION

anticipate all variations in actual end-use conditions, DuPont makes no warranties and assumes no liability in connection with any use of this information.

Regarding Medical Applications H-50102-3.

Copyright © 2009 DuPont. The DuPont Oval Logo, DuPont™, The miracles of science™, and trademarks designated with "®" are registered trademarks or trademarks of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.

This data sheet is effective as of 08/07/2010 05:44:02 PM and supersedes all previous versions.