

DuPont™ Surlyn® 1702-1

Surlyn® resins Product Data Sheet

**Description**

**Product Description** DuPont™ Surlyn® 1702-1 is an ionomer of ethylene acid copolymer.

The resin can be processed in conventional extrusion coating, blown film, cast film, sheet extrusion and coextrusion equipment designed to process polyethylene and ethylene copolymer type resins.

**Restrictions**

**Material Status** ● Commercial: Active

**Typical Characteristics**

**Composition** Zinc Ionomer

**Typical Properties**

Physical	Nominal Values	Test Method(s)	
* Density ( )	0.95 g/cm <sup>3</sup>	ASTM D792	ISO 1183
* Melt Flow Rate (190°C/2.16kg)	14 g/10 min	ASTM D1238	ISO 1133
Thermal	Nominal Values	Test Method(s)	
* Melting Point (DSC)	94°C (201°F)	ASTM D3417	ISO 3146
Freezing Point (DSC)	67°C (153°F)	ASTM D3417	ISO 3146
Vicat Softening Point ( )	65°C (149°F)	ASTM D1525	ISO 306

**Processing Information**

**General**

\* Maximum Processing Temperature 260°C (500°F)

General Processing Information Surlyn® 1702-1 is normally processed at melt temperatures ranging from 160°-235°C (320°-455°F) in blown, cast and extrusion coating equipment. Typical extruder profiles are below. Actual processing temperatures will usually be determined by either the specific equipment or substrate or one of the other polymers in a coextrusion.

Materials of construction used in the processing of this resin should be corrosion resistant. Stainless steels of the types 316, 15-5PH, and 17-4PH are excellent, as is quality chrome or nickel plating, and in particular duplex chrome plating. Type 410 stainless steel is satisfactory, but needs to be tempered at a minimum temperature of 600°C (1112°F) to avoid hydrogen-assisted stress corrosion cracking. Alloy steels such as 4140 are borderline in performance. Carbon steels are not satisfactory. While stainless steels can provide adequate corrosion

protection, in some cases severe purging difficulties have been encountered. Nickel plating has been satisfactory, but experiments have shown that chrome surfaces have the least adhesion to acid based polymers. In recent years, the quality of chrome plating has been deteriorating due to environmental pressures, and the corrosion protection has not always been adequate. Chrome over top of stainless steel seems to provide the best combination for corrosion protection and ease of purging.

If surface properties of the extruded resin require modification (such as, lower C.o.F. for packaging machine processing), refer to the Conpol™ Processing Additive Resins product information guide.

After processing Surlyn®, purge the material out using a polyethylene resin, preferably with a lower melt flow rate than the Surlyn® resin in use. The "Disco Purge Method" is suggested as the preferred purging method, as this method usually results in a more effective purging process. Information on the Disco Purge Method can be obtained via your DuPont Sales Representative.

Never shut down the extrusion system with Surlyn® in the extruder and die. Properly purge out the Surlyn® with a polyethylene, and shut down the line with polyethylene or polypropylene in the system.

<b>Blown Film Processing</b>	<b>Nominal Values</b>
Blown Film Processing Information	A suggested initial extruder temperature set profile.
Feed Zone	110°C (230°F)
Second Zone	135°C (275°F)
Third Zone	160°C (320°F)
Fourth Zone	160°C (320°F)
Fifth Zone	160°C (320°F)
Adapter Zone	160°C (320°F)
Die Zone	160°C (320°F)
<b>Cast Film / Sheet Processing</b>	<b>Nominal Values</b>
Cast Film / Sheet Processing	A suggested initial extruder temperature set profile.
Feed Zone	135°C (275°F)
Second Zone	185°C (365°F)
Third Zone	210°C (410°F)
Fourth Zone	210°C (410°F)
Fifth Zone	210°C (410°F)
Adapter Zone	210°C (410°F)
Die Zone	210°C (410°F)
<b>Extrusion Coating/Lamination Processing</b>	<b>Nominal Values</b>
Extrusion Coating / Lamination Processing	A suggested initial extruder temperature set profile.
Feed Zone	160°C (320°F)
Second Zone	210°C (410°F)
Third Zone	235°C (455°F)
Fourth Zone	235°C (455°F)
Fifth Zone	235°C (455°F)
Adapter Zone	235°C (455°F)
Die Zone	235°C (455°F)

177.1330(a) - Ionomeric resins, subject to the limitations and requirements therein. This Regulation describes polymers that may be used in contact with food, subject to the finished food-contact article meeting the extractive limitations under the intended conditions of use, as shown in paragraph (c) of the Regulation.

The information and certifications provided herein are based on data we believe to be reliable, to the best of our knowledge. The information and certifications apply only to the specific material designated herein as sold by DuPont and do not apply to use in any process or in combination with any other material. They are provided at the request of and without charge to our customers. Accordingly, DuPont cannot guarantee or warrant such certifications or information and assumes no liability for their use.

#### Regulatory Information

For information on regulatory compliance outside of the U.S., consult your local DuPont representative.

#### Safety & Handling

For information on appropriate Handling & Storage of this polymeric resin, please refer to the Material Safety Data Sheet.

A Product Safety Bulletin, Material Safety Data Sheet, and/or more detailed information on extrusion processing and/or compounding of this polymeric resin for specific applications are available from your DuPont Packaging and Industrial Polymers representative.

### Read and Understand the Material Safety Data Sheet (MSDS) before using this product

#### Regional Centres

DuPont operates in more than 70 countries. For help finding a local representative, please contact one of the following regional customer contact centers:

##### Americas

DuPont Company  
Chestnut Run Plaza – Bldg. 730  
974 Centre Road  
Wilmington, Delaware  
19805 U.S.A.  
Toll-Free (USA): 1-800-628-6208  
Telephone: 1-302-774-1000  
Fax: 1-302-355-4013

##### Asia Pacific

DuPont China Holding Co., Ltd.  
Shanghai Branch  
399 Keyuan Road, Bldg. 11  
Zhangjiang Hi-Tech Park  
Pudong New District, Shanghai  
P.R. China (Postcode: 201203)  
Telephone +86 21 3862 2888  
Fax +86-21-3862-2889

##### Europe / Middle East / Africa

DuPont de Nemours Int'l. S.A.  
2, Chemin du Pavillon Box 50  
CH-1218 Le Grand Saconnex  
Geneva, Switzerland  
Telephone +41 22 717 51 11  
Fax +41 22 717 55 00

DuPont do Brasil, S.A.  
Alameda Itapecuru, 506  
06454-080 Barueri, SP Brasil  
Telephone: +55 11 4166 8000  
Fax: +55 11 4166 8736

<http://surlyn.dupont.com>

*The data listed here fall within the normal range of properties, but they should not be used to establish specification limits nor used alone as the basis of design. The DuPont Company assumes no obligations or liability for any advice furnished or for any results obtained with respect to this information. All such advice is given and accepted at the buyer's risk. The disclosure of information herein is not a licence to operate under, or a recommendation to infringe, any patent of DuPont or others. Since DuPont cannot anticipate all variations in actual end-use conditions, DuPont makes no warranties and assumes no liability in connection with any use of this information.*

**CAUTION:** Do not use DuPont materials in medical applications involving implantations in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract that is consistent with DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative. You may also request a copy of DuPont POLICY Regarding Medical Applications H-50103-3 and DuPont CAUTION Regarding Medical Applications H-50102-3.

Copyright © 2009 DuPont. The DuPont Oval Logo, DuPont™, The miracles of science™, and trademarks designated with "®" are

*registered trademarks or trademarks of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.*

*This data sheet is effective as of 05/08/2012 09:06:54 PM and supersedes all previous versions.*