

DuPont™ Kalrez®

Physical Properties and Product Comparisons for Aircraft/Aerospace

Technical Information — January 2018

DuPont™ Kalrez® perfluoroelastomer parts are available in a number of different products that have been formulated to optimize properties in order to give the best possible performance. Modification of finished properties is achieved through the use of fillers and other additives. Descriptions of the key attributes of each product and its general area of application are listed below.

Typical Physical Properties¹

Property	Kalrez® 4079AMS	Kalrez® AeroSeal™ 7777	Kalrez® AeroSeal™ 7797
Color	Black	Black	Black
Hardness, Shore A ²	75	75	90
50% Modulus ³ , MPa (psi)	—	—	15.91 ³ (2310)
100% Modulus ⁴ , MPa (psi)	7.24 (1050)	7.58 (1100)	—
Tensile Strength at Break ⁴ , MPa (psi)	16.88 (2450)	17.91 (2600)	23.84 ³ (3460)
Elongation at Break ⁴ , %	150	160	77 ³
Compression Set ⁵ 70 hr at 204 °C, %	25	12	11 ⁶
Temperature of Retraction, Tr10 ⁷ , °C	-2	-4	-5 ⁸
Maximum Service Temperature ⁹ , °C	316	325	325

1 Not to be used for specification purposes.

2 ASTM D2240 (pellet test specimens)

3 ASTM D1414 and ASTM D412 (AS568 K214 O-ring test specimens)

4 ASTM D412 (dumbbell test specimens)

5 ASTM D395B (pellet test specimens)

6 ASTM D1414 and D395B (AS568 K214 O-ring test specimens test specimens)

7 ASTM D1329 (dumbbell test specimens)

8 ASTM D1329 (dumbbell test specimens stretched 25%)

9 DuPont proprietary test method

Kalrez® 4079AMS

Kalrez® 4079AMS is a specialty black product that meets the requirements of Aerospace Material Specification (AMS) 7257. It offers outstanding thermal stability, excellent compression set resistance and good seal force retention properties. It also offers excellent resistance to HTS (High Thermo-Oxidative Stability) gas turbine engine lubricating oils and has good response to temperature cycling effects. Kalrez® 4079AMS has good mechanical properties and is well suited for both static and dynamic sealing applications. A maximum service temperature of 316 °C (600 °F) is suggested. Short excursions to higher temperatures may also be possible.



The miracles of science™

DuPont™ Kalrez® AeroSeal™ 7777

Kalrez® AeroSeal™ 7777 is a specialty black product that offers outstanding thermal stability and compression set resistance along with excellent seal force retention properties. It also offers excellent resistance to HTS (High Thermo-Oxidative Stability) gas turbine engine lubricating oils and has excellent response to temperature cycling effects. Kalrez® AeroSeal™ 7777 has good mechanical properties and is well suited for both static and dynamic sealing applications. A maximum service temperature of 325 °C (617 °F) is suggested. Short excursions to higher temperatures may also be possible.

Kalrez® AeroSeal™ 7797

Kalrez® AeroSeal™ 7797 is a specialty black product specifically targeted for use in applications requiring higher hardness/higher modulus properties. It offers outstanding thermal stability and compression set resistance and has excellent seal force retention properties. It also offers excellent resistance to HTS (High Thermo-Oxidative Stability) gas turbine engine lubricating oils and has excellent response to temperature cycling effects. Kalrez® AeroSeal™ 7797 has excellent mechanical properties and is well suited for both static and dynamic sealing applications. A maximum service temperature of 325 °C (617 °F) is suggested. Short excursions to higher temperatures may also be possible.

Other Properties

Other properties, such as coefficients of friction, thermal conductivity, electrical, permeability, etc., may be of interest for specific applications. For more detailed information, please refer to the specific aerospace product in the Kalrez® Application Guide (KAG) for aircraft/aerospace www.kalrez.com.

Product Safety

Highly toxic products can be generated when Kalrez® parts are exposed to fire or temperatures in excess of 400 °C so respiratory equipment should be used if ventilation is inadequate. Kalrez® parts are incompatible and should not be exposed to alkali metals or interhalogen products. Please consult the "Guide For Safety In Handling Kalrez® Perfluoroelastomer Parts" (KZE-A10301) for additional information.

Visit us at kalrez.dupont.com

Contact DuPont at the following regional locations:

North America 800-222-8377	Latin America +0800 17 17 15	Europe, Middle East, Africa +41 22 717 51 11
Greater China +86-400-8851-888	ASEAN +65-6586-3688	Japan +81-3-5521-2960

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise.

The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use and disposal conditions, DuPont does not guarantee favorable results, makes no warranties and assumes no liability in connection with any use of this information. All such information is given and accepted at the buyer's risk. It is intended for use by persons having technical skill, at their own discretion and risk. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent. DuPont advises you to seek independent counsel for a freedom to practice opinion on the intended application or end-use of our products.

CAUTION: Do not use DuPont materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract that is consistent with DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative. You may also request a copy of DuPont POLICY Regarding Medical Applications H-50103-5 and DuPont CAUTION Regarding Medical Applications H-50102-5.

Copyright © DuPont. The DuPont Oval Logo, DuPont™, The miracles of science™, and Kalrez®, and Zalak® are trademarks or registered trademarks of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.

(02/06) Reference No. KZE-A10444-00-F0118

