

# AURUM<sup>®</sup> J-1548

## THERMOPLASTIC RESIN FOR HIGH-LOAD APPLICATIONS

AURUM<sup>®</sup> J-1548 resin is specified for high temperature hostile environments requiring high mechanical properties and low wear and friction performance. J-1548 resin is produced from filled thermoplastic polyimide (TPI) composition.

### Typical Properties of AURUM<sup>®</sup> J-1548

Mechanical Property	Temperature	Test Method	Units	Typical Values
Tensile Strength	23 °C (73 °F) 150 °C (302 °F)	ASTM D638	MPa (kpsi)	252 (36.5) 119 (17.3)
Elongation at Break	23 °C (73 °F) 150 °C (302 °F)	ASTM D638	%	2.0 2.0
Flexural Strength	23 °C (73 °F)	ASTM D790	MPa (kpsi)	354 (51.3)
Flexural Modulus	23 °C (73 °F)	ASTM D790	GPa (kpsi)	20.4 (2,900)
Notched Izod 3.2 mm (0.13 in)	23 °C (73 °F)	ASTM D256	J/m (ft-lb/in)	106 (2.0)
<b>Thermal Property</b>				
HDT at 1.8 MPa (264 psi)		ASTM D648	°C (°F)	236 (457)
CTE Flow Direction	23–150 °C (73–302 °F)	ASTM E228	ppm/°C (ppm/°F)	11 (6)
CTE Transverse Direction	23–150 °C (73–302 °F)	ASTM E228	ppm/°C (ppm/°F)	37 (21)
<b>Wear and Friction</b>				
PV Limit (Dry)*		DuPont	MPa m/s (kpsi-fpm)	4.0 (115)
Coefficient of Friction (Dry)*		DuPont		0.09
<b>Other Properties</b>				
Specific Gravity	23 °C (73 °F)	ASTM D792		1.39
Water Absorption, 24 hr	23 °C (73 °F)	ASTM D570	%	0.08

\*Internal test method. Baldwin block on ring equipment. Pressure from 1.0 to 6.3 MPa (145 to 870 psi) against SUS440C.

Visit us at [vespel.dupont.com](http://vespel.dupont.com)

---

Contact DuPont at the following regional locations:

**North America**

800-222-8377

**Latin America**

+0800 17 17 15

**Europe, Middle East, Africa**

+41 22 717 51 11

**Greater China**

+86-400-8851-888

**ASEAN**

+65-6586-3688

**Japan**

+81-3-5521-8484

---

*The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise.*

*The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use and disposal conditions, DuPont does not guarantee favorable results, makes no warranties and assumes no liability in connection with any use of this information. All such information is given and accepted at the buyer's risk. It is intended for use by persons having technical skill, at their own discretion and risk. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent. DuPont advises you to seek independent counsel for a freedom to practice opinion on the intended application or end-use of our products.*

*CAUTION: Do not use DuPont materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract that is consistent with DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative. You may also request a copy of DuPont POLICY Regarding Medical Applications H-50103-5 and DuPont CAUTION Regarding Medical Applications H-50102-5.*

*Copyright© 2017 DuPont. The DuPont Oval Logo and DuPont™ are trademarks or registered trademarks of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.*

*AURUM® is a registered trademark of Mitsui Chemicals, Inc.*

*VPE-A10974-00-B0711 (8/17)*

