

Rigid Foam Insulation in Concrete Sandwich Panel Applications

SYSTEM OVERVIEW

General Information

The unique properties of DuPont™ Styrofoam™ Brand SM insulation and Styrofoam™ Brand Perimate™ insulation give them exceptionally good qualities for a wide variety of uses. In particular, Styrofoam™ Brand insulation products outperform all other products in exterior foundation applications.


Advantages

There are several advantages to insulating the exterior surface of foundation walls. The block or concrete wall insulated on the exterior surface is not subjected to large temperature differences and so will not act as a thermal bridge. Block walls insulated on the exterior undergo less air convection in block cavities. At nearly room temperature, the basement walls act as a heat reservoir, buffering interior temperature fluctuations. In some instances, adfreezing forces are prevented from acting directly on the basement wall. And finally, unlike interior applications, no living space is lost.

Design Considerations

Insulation

The use of Styrofoam™ Brand SM insulation meeting CAN/ULC S701 Type 4 is recommended. Where additional drainage is required, Styrofoam™ Brand Perimate™ insulation meeting CAN/ULC S701 Type 4 should be considered. The insulation boards are applied vertically to the wall (horizontally for slab on grade or shallow foundation applications) and are secured at the top with a compatible adhesive or by nailing to the wall. Backfilling against the insulation will hold the lower portion of the boards in place. The insulation should extend from the top of the foundation wall to the top of the footing. Styrofoam™ Brand Perimate™ insulation is a CCMC Class A Type 2 drainage layer.



Waterproofing and Damp-Proofing

Waterproofing and damp-proofing materials should not be used for adhering the insulation. The insulation should be installed once the damp-proofing has cured sufficiently, as the solvents in some of these materials may attack polystyrene insulation.

Protective Covering

It is important that the above-grade portion of Styrofoam™ Brand SM insulation be protected from physical damage and direct exposure to sunlight (i.e., ultraviolet degradation). Depending on the extent of protection needed, your options include a cementitious or thin stucco coating, application of a fiberglass reinforced plastic or vinyl sheet, or a metallic covering. Flashing should be installed over the top edge of the insulation and protective covering.

TABLE 1: Physical Properties of Styrofoam™ Brand SM Insulation and Styrofoam™ Brand Perimate™ Insulation

Property and Test Method	Value
Thermal Resistance ⁽¹⁾ per in. (25 mm), ASTM C518, C177, 75°F (24°C) mean temp., ft ² ·h·°F/Btu (m ² ·°C/W), R-value (RSI), min.	5.0 (.87)
Compressive Strength ⁽²⁾ , ASTM D1621, psi (kPa), min.	30 (210)
Water Absorption, ASTM D2842, % by volume, max.	0.7
Maximum Use Temperature, °F (°C)	165 (74)
Coefficient of Linear Thermal Expansion, ASTM D696, in/in·°F (mm/mm·°C)	3.5 x 10 ⁻⁵ (6.3 x 10 ⁻²)

⁽¹⁾ Values are consistent with criteria of ASTM C578.

⁽²⁾ Vertical compressive strength is measured at 10 percent deformation or at yield, whichever comes first. Since Styrofoam™ Brand extruded polystyrene insulations are visco-elastic materials, adequate design safety factors should be used to prevent long-term creep and fatigue deformation. For static loads, 3:1 is suggested. For dynamic loads, 5:1 is suggested.

INSTALLATION

Slab On Grade Insulation

The use of DuPont™ Styrofoam™ Brand SM insulation is recommended. The insulation boards are applied vertically to the inside of the foundation wall and are initially secured at the top with an adhesive compatible with polystyrene insulation based on CGSB specification #71- GP-24M. Backfilling against the insulation will hold the boards firmly in place. The insulation should extend from the bottom of the floor slab to the top of the footing.

Vapour Barrier

The vapour barrier, if used, should be installed along the underside of the floor slab and over the top edge of the insulation.

Under Slab

The use of Styrofoam™ Brand SM insulation is recommended except where the slab will be expected to sustain very high loading (from mechanical equipment, etc.). In that case, a higher-compressive strength insulation should be considered, such as Styrofoam™ Brand Highload 40, 60 or 100 insulation.

The insulation boards should be placed snugly around the perimeter of the foundation wall and laid directly over the well-compacted porous fill. The insulation is laid loose with



the edges butted tightly together. However, if wind uplift may be a problem before the concrete slab is poured, secure the insulation boards to the ground with 6 mm (1/4") diameter wood skewers which should be at least 75 mm (3") longer than the thickness of the Styrofoam™ Brand insulation.

Vapour Barrier

The vapour barrier, if used, is laid over the top of the insulation and under the entire floor slab area.

Weepers

Weepers should be included on the inner face of the foundation wall if the soil conditions do not provide sufficient drainage.



For more information visit
building.dupont.com
 or call 1-866-583-2583

NOTICE: No freedom from any patent owned by DuPont or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where DuPont is represented. The claims made may not have been approved for use in all countries or regions. DuPont assumes no obligation or liability for the information in this document. References to "DuPont" or the "Company" mean the DuPont legal entity selling the products to Customer unless otherwise expressly noted. NO EXPRESS WARRANTIES ARE GIVEN EXCEPT FOR ANY APPLICABLE WRITTEN WARRANTIES SPECIFICALLY PROVIDED BY DUPONT. ALL IMPLIED WARRANTIES INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED. The buyer assumes all risks as to the use of the material. Buyer's exclusive remedy or any claim (including without limitations, negligence, strict liability, or tort) shall be limited to the refund of the purchase price of the material. Failure to strictly adhere to any recommended procedures shall release DuPont Specialty Products USA, LLC or its affiliates, of all liability with respect to the materials or the use thereof. The information herein is not intended for use by non-professional designers, applicators or other persons who do not purchase or utilize this product in the normal course of their business.

CAUTION: When cured, these products are combustible and will burn if exposed to open flame or sparks from high-energy sources. Do not expose to temperatures above 240°F (116°C). For more information, consult (Material) Safety Data Sheet ((M)SDS), call DuPont at 1-866-583-BLUE (2583) or contact your local building inspector. In an emergency, call 1-989-636-4400 in the U.S. or 1-519-339-3711 in Canada. The blowing agent contained within this product can exhibit vapor flame limits under the right conditions. If specific operating conditions are such that concentrations of the blowing agent above the lower flammable limit can accumulate in areas with high relative humidity and in the presence of high-energy electrical discharges or other ignition sources, additional measures such as increased ventilation or coded electrical equipment (class one, division two) may be warranted. DO NOT SMOKE DURING USE. DO NOT USE NEAR ANY OPEN FLAME OR ELECTRICAL SOURCE. OUTDOOR USE ONLY. INDOOR USE INCREASES LIKELIHOOD OF IGNITABLE CONDITIONS. Read the label and (Material) Safety Data Sheet ((M)SDS) carefully before use. Wear gloves, and goggles or safety glasses. Provide adequate ventilation or wear proper respiratory protection. Contents under pressure. For outside use only.

Building and/or construction practices unrelated to insulation could greatly affect moisture and the potential for mold formation. No material supplier including DuPont can give assurance that mold will not develop in any specific system.

DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, ℠ or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted. © 2019 DuPont.